

Test Report

Photographic Activity Test according to ISO 18916:2007-06

Summary: The material described below has **passed** the criteria for enclosure materials defined in ISO 18916:2007 "Photographic activity test for enclosure materials".

PTS Test-Report: **35445**
Material description: **archival paper 0102 transparent - Archivpapier 0102 transparent**
Supplied by: **Walter Klug GmbH & Co. KG** on **16.02.2022**
Zollstraße 2, 87509 Immenstadt

Test Results

1. Image Interaction Test

The material shall not produce a percentage image interaction effect in the colloidal silver fade detectors greater than a relative difference of more than $\pm 20\%$ compared to the control.

Density change of control: **-1,25**
Density change of material: **-1,24** Relative difference: **1%**

2. Stain Test

The material shall not produce a mean stain in the photographic paper stain detector that is greater than the mean stain produced by the filter paper controls plus 0.08 density units.

Density change of control: **0,16**
Density change of material: **0,17** Difference: **0,01**

3. Mottle Test

The enclosure material shall not produce *easily recognizable* mottling.


Visual assessment: **Passed**

Date of testing: **23.03.2022** Sample-ID: **021-16**

Papiertechnische Stiftung
Pirnaer Straße 37, D-01809 Heidenau, Germany

*Papiertechnische Stiftung is
accredited according to
ISO/IEC 17025.*

 **DAKKS**
Deutsche
Akkreditierungsstelle
D-PL-17375-01-00



Dr.-Ing. Birgit Lutsch
Lab. Manager Materials Testing



Nicole Brandt
PAT Project Manager


PAT
ISO 18916